船用光缆 Marine Fiber Optic cable

HF Flame Oil Cold UV


AIOI-FL

应用 Application

本规范涵盖了船舶和移动海上平台通信和设备中使用的阻燃光缆的要求。

This specification covers the requirements for flame retardant optical cables used in communication and equipment of ships and mobile offshore platforms.

结构 Construction



光纤 Fiber	紧套光纤 颜色：参照 EIA/TIA 598-C	Tight Buffer Glass Fiber Color：Follow EIA/TIA 598-C
加强件 Strength Member	芳纶	Aramid yarn
内护套 Inner Sheath	SHF1	SHF1
铠装 Armored	镀锡铜丝编织，覆盖率≥90%	Tinned Copper Wire Braiding，Coverage≥90%
外护套 Outer Sheath	SHF1 颜色：黑色或定制	SHF1 Color ： Black or as customer's request
印字 Marking	Hysin □ MARINE □ Cable □ AIOI □ FL □ （ Number of Fibers ） □ (Fiber type) □ IEC60332-3-22□****m□xxxxxx□WW/YY 注：□ 表示空格；****m 表示计米；xxxxxx 表示批号;WW/YY 表示周数/年份 Note:□ means blank;****m means meters;xxxxxx means batch number;WW/YY means week/year	

光纤性能 Optical Characteristics

光纤类型 Fiber Type		SM 9/125 OS2 B1.3	MM 62.5/125 OM 1 A1b	MM 50/125 OM 2 A1a	MM 50/125 OM 3 A1a.2	MM 50/125 OM 4 A1a.3	MM 50/125 OM 5 A1a.4
纤芯直径 Core Diameter(μm)		9.2 ±.0.4	62.5 ± 2.5	50 ± 2.5	50 ± 2.5	50 ± 2.5	50 ± 2.5
衰减系数 Attenuation (dB/km)	@1310 nm	<0.40	-	-	-	-	-
	@1550 nm	<0.30	-	-	-	-	-
	@ 850 nm	-	<3.50	<3.00	<3.00	<3.00	<3.00
	@ 1300 nm	-	<1.00	<1.00	<1.00	<1.00	<0.70
带宽 Bandwidth (MHz*km)	@ 850 nm	-	>200	>500	>1500	>3500	>3500
	@ 1300 nm	-	>500	>500	>500	>500	>500
光纤容量 Fiber capacity 1GBase	SR 1310nm	10000m	-	-	-	-	-
	LX 1550nm	40000m	-	-	-	-	-
	SX 850nm	-	275 m	550 m	1000 m	1100 m	-
光纤容量 Fiber capacity 10GBase	SR 850nm	-	33 m	82 m	300 m	550 m	550 m
光纤容量 Fiber capacity 40GBase	SR 850nm	-	-	-	100 m	150 m	440m
光纤容量 Fiber capacity 100GBase	SR 850nm	-	-	-	-	-	150 m
Proof test(kpsi)		>100	>100	>100	>100	>100	>100

性能 Performances

存储/工作温度	Storage/Operating Temperature	-40℃ to + 85℃
衰减	Attenuation	IEC60793-1-40 & IEC60794-2
机械物理性能	Mechanical and particular characteristic	IEC60092-360
抗拉强度	Tensile strength	IEC60794-1-2 E1
抗压	Crush	IEC60794-1-2 E3
冲击	Impact	IEC60794-1-2 E4
扭转	Torsion	IEC60794-1-2 E7
弯曲	Cable bend	IEC60794-1-2 E11
阻燃性	Flame resistance	IEC 60332-3-22 Cat A
耐油	Oil resistance (SHF1)	IRM902, 70℃×4H
卤酸气体	Acid Gas Release Mounts	≤5mg/g （IEC 60754-1）
燃烧气体 PH 值	Burning Occur Gas Acidity	PH≥4.3 （IEC 60754-2）
燃烧气体导电率	Burning Occur Gas conductivity	<10 μS/mm (IEC 60754-2)
烟密度	Smoke density	≥60%（IEC 61034-2）
抗紫外线	UV resistance	UL1581
抗张强度 长期/短期	Tensile Strength Long/Short Term	600/1500 N
抗压性 长期/短期	Crush Resistance Long/Short Term	1000/3000 N/100mm

光纤颜色 Fiber Color code

光纤芯数 Fiber cores	2	4	6	8	12	16	24
光纤颜色 Color of fibers	BL OR	BL/OR GR/BR	BL/OR/GR BR/SL/WH	BL/OR/GR/BR SL/WH/RD/BK	BL/OR/GR/BR SL/WH/RD/BK YL/VI/RS/AQ	BL/OR/GR/BR SL/WH/RD/BK YL/VI/RS/AQ *BL/*OR/*GR/*BR	BL/OR/GR/BR SL/WH/RD/BK YL/VI/RS/AQ *BL/*OR/*GR/*BR *SL/*WH /*RD/*BK *YL/*VI/*RS/*AQ

※ The color comply with TIA-568/TIA-598

BL-Blue,OR-Orange,GR-Green,BR-Brown,SL-Slate,WH-White,RD-Red,BK-Black,YL-Yellow,VI-Violet,RS-Rose,AQ-Aqua

※The other color of fiber may be applicable when purchaser required.

技术参数 Technical Parameters

Type 型号	**Fiber Count 光纤芯数**	**Inner sheath Diameter 内护套外径 （mm）**	**Bending Radius Static/Dynamic 弯曲半径 静态/动态 (mm)**	**Outer sheath thickness 外护套厚度 （mm）**	**Outer Diameter 外护套外径 （mm）**
AIOI-FL	2~6	5.2±0.8	10D/20D	≥1.0	8.5±1.0
	8~12	6.2±0.8	10D/20D	≥1.0	9.5±1.0
	14~24	8.2±0.8	10D/20D	≥1.0	11.5±1.0

FL means Flame retardant.